

AGGREGATE GRADING & MOISTURE CONTENT TEST CERTIFICATE
BS EN 933-1:2012 & 1097-5:2008

Sampled By JOC

Road Number

Location Sampled from stockpile at source

Material Type Type 1 Ecoblend GA

Date Sampled 11/05/2018

Material Spec. SHW Clause 803

Date Received 11/05/2018

Date Tested 22/05/2018

Sieve	Passing %	Specification
63mm	100	100
40mm	98	-
31.5mm	91	75 - 99
25mm	84	-
20mm	78	-
16mm	71	43 - 81
10mm	55	-
8mm	48	23 - 66
6.3mm	42	
4mm	32	12 - 53
2mm	24	6 - 42
1.0mm	19	3 - 32
0.5mm	15	-
0.25mm	12	-
0.125mm	9	-
0.063mm	7.6	0 - 9.0
Grading of individual batches		
16 – 8mm	23	7 - 30
8 – 4mm	16	7 - 30
Method of Sieving	Wet By Difference	
Moisture Content %	7	

Aggregate Description: Mixed crushed aggregates

Remarks : Sample complies with the grading requirements.

Client Name Day Aggregates
F.A.O. Mr L Reid
Transport Avenue
Great Western Road
Brentford
Middlesex
Postcode TW8 9HQ

Signed :
Date : 29/05/2018

Authorised Signatories

P Parker / M Bustin	Compliance Team Leaders	J Nicholls	Senior Technician
J Tanzilli	Laboratory Team Leader	J Durrant	Senior Technician